



POLYTONE SYNTHETIC RESINS Modified Phenolic Resins

TECHNICAL DATA	POLYTONE P 144
Chemical Classification	Rosin Modified Penta Esterified, Phenol Formaldehyde Resin
Physical Form	Broken Lumps
Colour	Yellowish-Brown
Melting Point (Capillary)	145° C – 160 ° C
Viscosity of 30% solution in Toluene at 30° C by B 4 Ford Cup	19 - 24 sec
Acid Value	30 mg KOH/ g resin (Max)
MTO Tolerance of 50% solution in Toluene	1:15 Min

Properties & Usage

POLYTONE P 144 is a high melting, high molecular weight modified Phenolic resin suitable for the manufacture of high grade quickset / sheet fed inks - imparting excellent gloss and giving sharp prints with excellent press stability. POLYTONE P 144 is ideally suited for heat set inks because of its solubility in aliphatic hydrocarbon solvents.

Industrial Applications

Offset Printing Inks, Flexographic Inks, Gravure Inks, Printing Inks, Heat Set Inks Varnishes and many more

Solubility

POLYTONE P 144 gives good solubility with Aliphatic Hydrocarbons. It is completely soluble with Aromatic Hydrocarbons, Esters and Varnish Oils

Packaging

Available in 25 Kg bags

Shelf Life

Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred.

