

POLYTONE™ SYNTHETIC RESINS

Ketone Formaldehyde Resin

| TECHNICAL DATA | POLYTONE™ K 94 |
|---|----------------------------------|
| Chemical Classification | Cyclohexanone Formaldehyde Resin |
| Physical Form | Pearl Shaped Granular Solid |
| Melting Point (Capillary) | 90° C – 95 ° C |
| Viscosity of 50% solution in Industrial Spirit at 25° C by B 4 Ford Cup | 17 - 19 sec |
| Iodine No of 50% solution in Industrial Spirit | 1.0 Max |
| Hydroxyl Value | 200-220 mg KOH / gm resin |
| Acid Value | 1 mg KOH / gm resin (Max) |

Properties & Usage

POLYTONE™ K-94 is practically acidless, unsaponifiable Ketone Formaldehyde Resin which is very light in colour, has excellent light resistance and show but very slight tendency to solvent retention. Addition of this resin in general improves gloss, hardness, filling, adhesive strength and durability. POLYTONE K-94 is available in pearl shaped granules. This resin is highly effective in imparting gloss, adhesiveness in the inks and also in increasing the solid content in flexo & gravure inks. Use of this resin in ball point pen inks ensure that pastes and inks in writing instruments do not dry quickly yet set quickly after writing. POLYTONE K-94 is used in the manufacture of all types of nitrolacquers and is most suitable for paper lacquers. This resin is useful in the manufacture of PVC lacquers and for polishing lacquers and finishes for the surface treatment of wooden furniture and articles.

Industrial Applications

Flexographic Inks, Gravure Inks, Lamination Inks, Ball Point Inks, Lacquers, Offset Inks, PU-systems, Nitro Cellulose Paints, Varnishes, Heat Seal Coating, Primer and Base Coatings, Gasoline resistant coatings, Nail Lacquers and many more

Solubility

POLYTONE™ K-94 is soluble in alcohols(not in methanol), ketones, esters, glycol ether acetates, as well as in some aromatic & chlorinated hydrocarbons. It is however not soluble in water and in aliphatic hydrocarbons.

Compatibility

POLYTONE™ K-94 is compatible with different types of nitrocellulose, benzyl cellulose, ethyl cellulose, cellulose acetate, polyvinyl chloride, chlorinated rubber, as well as in many synthetic resins e.g. alkyd resins, phallic resins, UF resins, polyvinyl butyryl resins, polyamide, phenol formaldehyde condensation resins etc and a multitude of plasticizers.

Packaging

Available in 25 Kg bags

Shelf Life

Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture