

POLYTONE™ SYNTHETIC RESINS **Modified Maleic Resins**

TECHNICAL DATA

POLYTONE™ M 136

Chemical Classification	Rosin Modified Maleic Resin
Type	Spirit Soluble
Physical Form	Broken Lumps
Colour	Yellow
Melting Point (Capillary)	125° C – 135 ° C
Viscosity of 50% solution in Industrial Spirit at 30° C by B 4 Ford Cup	28 - 33 sec
Acid Value	125 – 135 mg KOH/ g resin (Max)

Application POLYTONE™ M 136 is used in Paper Varnishes, Liquid Inks etc.

Solubility POLYTONE™ M 136 is soluble in Spirit.

Packaging Available in 25 Kg bags

Shelf Life Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture