

POLYTONE SYNTHETIC RESINS Modified Phenolic Resins

| TECHNICAL DATA | POLYTONE P 144 |
|---|--|
| Chemical Classification | Rosin Modified Penta Esterified, Phenol Formaldehyde Resin |
| Physical Form | Broken Lumps |
| Colour | Yellowish-Brown |
| Melting Point (Capillary) | 145° C – 160 ° C |
| Viscosity of 30% solution in Toluene at 30° C by B 4 Ford Cup | 19 - 24 sec |
| Acid Value | 30 mg KOH/ g resin (Max) |
| MTO Tolerance of 50% solution in Toluene | 1:15 Min |

Properties & Usage

POLYTONE P 144 is a high melting, high molecular weight modified Phenolic resin suitable for the manufacture of high grade quickset / sheet fed inks - imparting excellent gloss and giving sharp prints with excellent press stability. POLYTONE P 144 is ideally suited for heat set inks because of its solubility in aliphatic hydrocarbon solvents.

Industrial Applications

Offset Printing Inks, Flexographic Inks, Gravure Inks, Printing Inks, Heat Set Inks Varnishes and many more

Solubility

POLYTONE P 144 gives good solubility with Aliphatic Hydrocarbons. It is completely soluble with Aromatic Hydrocarbons, Esters and Varnish Oils

Packaging

Available in 25 Kg bags

Shelf Life

Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture

POLYTONE™ SYNTHETIC RESINS Modified Phenolic Resins

TECHNICAL DATA

POLYTONE™ P 148

| | |
|---|---|
| Chemical Classification | Rosin Modified Penta Esterified, Phenol Formaldehyde Resin |
| Physical Form | Yellowish Solid Lumps |
| Colour (30% Solution in Toluene) | 12 MAX [Gardner Scale] |
| Melting Point (Capillary) | 130° C – 150 ° C |
| Viscosity of 35% solution in ARLO at 25° C | 60 – 100 Poise |
| Acid Value | 25 mg KOH/ g resin (Max) |
| MTO Tolerance of 30% solution in Toluene | 1:7 Min |

Properties & Usage

POLYTONE™ P 148 is a high melting, high molecular weight modified Phenolic resin suitable for the manufacture of high grade quickset / sheet fed inks - imparting excellent gloss and giving sharp prints with excellent press stability. POLYTONE™ P 148 is ideally suited for heat set inks because of its solubility in aliphatic hydrocarbon solvents.

Industrial Applications

Offset Printing Inks, Flexographic Inks, Gravure Inks, Printing Inks, Heat Set Inks Varnishes and many more

Solubility

POLYTONE™ P 148 gives good solubility with Aliphatic Hydrocarbons. It is completely soluble with Aromatic Hy Esters and Varnish Oils

Packaging

Available in 25 Kg bags

Shelf Life

Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture