



POLYTONE™ SYNTHETIC RESINS

Phenol Formaldehyde Resin

TECHNICAL DATA

POLYTONE™ PF 132 C

PART 1 /RESIN

Chemical Classification	Phenol Formaldehyde Resin
Physical Form	Lump (Part 1)
Color	Yellow to Reddish Brown
Melting Point (Capillary)	70° C – 85 ° C

PART 2/CATALYST

Physical Form	Crystalline Powder (Part 2)
Color	White

PART 1 + PART 2

Part 2 Catalyst / Hexa Content	7% - 9% of (Part 1 + Part 2)
Inclined Plate Flow@125° C	30 – 45 mm
Hot Plate Cure @ 160° C	40 – 65 sec

Properties & Usage

POLYTONE™ PF 132 C is a phenol – formaldehyde resin to be mixed with Hexa or Part 2 Catalyst. POLYTONE™ PF 132 C (Part 1 + 2) effortlessly penetrates and adheres to the structure of many organic and inorganic fillers and reinforcements which makes it an ideal candidate for various end uses.

Usage Suggestions :

- 1 .Part 1 should be powdered and mixed with Part 2 as per suggested loading quantity. Cured at necessary temperature.
2. Part 1 + Part 2 to be mixed and dissolved in Alcohol/Ketone to prepare a solution. Solution to be mixed with filler etc or applied on surface and cured.

Industrial

Molding Powder, Molding Compounds, Abrasive, Grinding Wheels, Binder, Foundry Binder, Housings,

P&P/TDS/POLYTONE™ PF132/REV000/23.06.2012
Copyright©2012 Polyols & Polymers Pvt.Ltd

● POLYOLS & POLYMERS PVT.LTD. ☒ C-1/58-59, GIDC, VAPI, GJ, INDIA ☎ info@polyolsandpolymers.net 🌐 www.polyolsandpolymers.net ●

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred.

POLYTONE™ is a trademark of Polyols & Polymers Pvt.Ltd. ● ISO 9001:2008 Certified



Applications

Laminates, Corrugated Box Manufacture, Ply Wood, Particle Board, Hard Board, Binder in Pyrotechnic Compositions and many more
Resin/ Part 1 is applicable in Ink Industry.

Solubility

POLYTONE™ AP 132 is soluble in alcohols, esters, ketones, aromatic and aliphatic chlorinated hydrocarbons.

Packaging

Available in 25 Kgs Standard Bags (Resin/Part 1)

Shelf Life

Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture (Resin/Part 1)

P&P/TDS/POLYTONE™ PF132/REV000/23.06.2012
Copyright©2012 Polyols & Polymers Pvt.Ltd

• POLYOLS & POLYMERS PVT.LTD. ✉ C-1/58-59, GIDC, VAPI, GJ, INDIA 🌐 info@polyolsandpolymers.net 🌐 www.polyolsandpolymers.net •

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred.

POLYTONE™ is a trademark of Polyols & Polymers Pvt.Ltd. • ISO 9001:2008 Certified