



POLYTONE™ SYNTHETIC RESINS Thermoplastic Acrylic Resins

TECHNICAL DATA

POLYTONE™ ABR-1012

Chemical Classification	Acrylic Polymer
Type	MMA Resin
Physical Form	Fine Granules or Beads
Colour	White
Glass Transition Temperature	98 ° C
Viscosity of 37.5% solution in Toluene at 25° C	33 – 37 Poises
Acid Value	0 mg KOH/ g resin
Molecular Weight	Medium

<u>Application</u>	POLYTONE™ ABR 1012 is used is general purpose grade for lacqueres such as barrier top coating of vinyl fabrics , clear lacquer for steel, ABS , Polysterene etc. Suitable for gravure inks. Very high tensile strength and hardness.
<u>Solubility</u>	POLYTONE™ ABR 1012 is soluble in Methylene & Ethylene Chloride, Methyl Formate, THF, Toluene, Ethyl, Isopropyl & N-Butyl Acetates, Cellosolve, MEK, DAA, Acetonitrile, Acetone ETC.
<u>Compatibility</u>	POLYTONE™ ABR 1012 is compatible with NC, Epoxy, Vinyl Chloride, Silicone, PTSF, Cumarone, Indone, Cellulose Acetate Butyrate Resins.
<u>Packaging</u>	Available in 20 Kg bags.
<u>Shelf Life</u>	Store under cool dry conditions . It is recommended that the material be used within 12 months from the date of manufacture.

P&P/TDS/POLYTONE™ ABR-1012/REV000/23.01.2017
Copyright©2017 Polyols & Polymers Pvt.Ltd.

● POLYOLS & POLYMERS PVT.LTD. ☒ C-1/58-59, GIDC, VAPI, GJ, INDIA ✉ info@polyolsandpolymers.net 🌐 www.polyolsandpolymers.net ●

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred. POLYTONE™ is a trademark of Polyols & Polymers Pvt.Ltd. ● ISO 9001:2008 Certified