

## POLYTONE™ SYNTHETIC RESINS Modified Maleic Resins

TECHNICAL DATA	POLYTONE™ M 135
Chemical Classification	Rosin Modified Maleic Resin
Type	Spirit Soluble
Physical Form	Broken Lumps
Colour	Yellow
Melting Point (Capillary)	105° C – 120 ° C
Viscosity of 50% solution in Industrial Spirit at 30° C by B 4 Ford Cup	18 - 23 sec
Acid Value	125 – 135 mg KOH/ g resin (Max)

<b><u>Application</u></b>	POLYTONE™ M 135 is used in Spirit soluble varnishes, N.C. Lacquers, Road Marking Paints, Liquid Inks etc
<b><u>Industrial Application</u></b>	Printing Inks, Offset Inks, Gravure Inks, Lamination Inks
<b><u>Solubility</u></b>	POLYTONE™ M 135 is soluble in Spirit.
<b><u>Packaging</u></b>	Available in 25 Kg bags
<b><u>Shelf Life</u></b>	Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture

P&P/TDS/POLYTONE™ M-135/REV001/21.12.2011  
Copyright©2011 Polyols & Polymers Pvt.Ltd.

● POLYOLS & POLYMERS PVT.LTD. ✉ C-1/58-59, GIDC, VAPI, GJ, INDIA 📧 [info@polyolsandpolymers.net](mailto:info@polyolsandpolymers.net) 🌐 [www.polyolsandpolymers.net](http://www.polyolsandpolymers.net) ●

The information contained herein is to the best of our knowledge, accurate and reliable. The information given herein is for reference only and is subjected to change without prior notice. However, as use conditions are not within our control no guarantees are given or are to be inferred, nor is freedom from any patent to be inferred.

POLYTONE™ is a trademark of Polyols & Polymers Pvt.Ltd. ● ISO 9001:2008 Certified