

POLYTONE™ SYNTHETIC RESINS **Modified Maleic Resins**

| TECHNICAL DATA | POLYTONE™ M 136 |
|---|---------------------------------|
| Chemical Classification | Rosin Modified Maleic Resin |
| Type | Spirit Soluble |
| Physical Form | Broken Lumps |
| Colour | Yellow |
| Melting Point (Capillary) | 125° C – 135 ° C |
| Viscosity of 50% solution in Industrial Spirit at 30° C by B 4 Ford Cup | 28 - 33 sec |
| Acid Value | 125 – 135 mg KOH/ g resin (Max) |

| | |
|---------------------------|--|
| <u>Application</u> | POLYTONE™ M 136 is used in Paper Varnishes, Liquid Inks etc. |
| <u>Solubility</u> | POLYTONE™ M 136 is soluble in Spirit. |
| <u>Packaging</u> | Available in 25 Kg bags |
| <u>Shelf Life</u> | Store under cool dry conditions. It is recommended that the material be used within 12 months from the date of manufacture |